DualMirror II P-202 58"

General Information

Item ID	1100391
Style	P-202
Finish / Coating	DualMirror II MLA

Construction

Fiber Type	PBI/Aramid
Weave	Mock Knit

Physical Properties	US	Metric	Tolerance
Weight	7.5 oz/yd2	251 g/m2	± 10%
Thickness	24 mils	0.61 mm	± 10%
Width(s)	58.00 in	147.00 cm	+ 1" / - 0.5"
Length	50.00 yards	45.72 m	± 10%

Thermal Properties	US	Metric
Radiant Temperature	3000 ˚F	1648 ˚C

Testing	US	Metric
Tensile Strength ASTM D5035	Warp - 216 lbf Weft - 251 lbf	Warp – 960.8 N Weft – 1116.5 N
Tear Strength ASTM D5587	Warp - 67 lbf Weft - 65 lbf	Warp - 298 N Weft - 289 N
Radiant Performance ASTM F2702 (time to second degree burn)	55 sec	55 sec