Phone: (585) 924-9135 or (800) 836-1001 | Technical Dept: tech@newtex.com | Website: www.newtex.com

DualMirror II R-480 58" Rayon

General Information	
Item ID	1100396
Style	R-480
Finish / Coating	Z-Flex MLA

Construction	
Fiber Type	Rayon
Weave	Herringbone
Ends x Picks	45 X 23

Physical Properties	US	Metric
Weight	15.00 oz/yd^2	509 g/m^2
Thickness	30 mils	0.76 mm
Width(s)	58 in	152 cm
Length	50 yards	45.72 m

Thermal Properties	US	Metric
Radiant Temperature	3000 °F	1650 °C

Testing		
Abrasion ASTM D3884-90	2000+ Cycles	
Tensile Strength ASTM D5093	Warp – 283 lbf Weft - 164 lbf	1259 N 728 N
Tear Strength ASTM D5587	Warp – 25 lbf Weft - 26 lbf	113 N 116 N
Radiant Performance ASTM 2707 [Time to second degree burn]	32.96 s	