
Item Description	DualMirror II 1006 40" HB
Item ID	1130203
Weight (oz/yd ²)	15.0
Thickness (mils)	30.0
Width (in)	40.0

Construction

Fiber Type	Rayon
Weave	Herringbone
Ends x Picks	34 x 24
Finish/Coating	DualMirror II Aluminized
Tear Strength (lbf)	25.0

Temperature Ratings

Operating Temp (°F)	220.0
Peak Temp (°F)	375.0

Radiant & Molten Protection

Radiant Protection (ASTM 1939)	>30
Radiant Resistance (ISO 11612)	C4
Molten Aluminum (ISO 11612)	D3
Molten Iron (ISO 11612)	E3

Ordering Information

Roll Length (yards)	50.0
Minimum Order Quantity	50 Yards

Questions?

Please call Technical Sales Support or email us at sales@newtex.com

USA (585) 924-9135

INT (800) 836-1001