

Item Description	DualMirror II 1006 60" Rayon HB
Item ID	1130234
Weight (g/m2)	510.0
Thickness (mm)	0.76

Construction

Fiber Type	Rayon
Weave	Herringbone
Ends x Picks	34 x 24
Finish/Coating	DualMirror II Aluminized
Tear Strength (N)	110.0

Temperature Ratings

Operating Temperature (°C)	105.0
Peak Temperature (°C)	190.0

Radiant & Molten Protection

Radiant Protection (ASTM 1939)	>30
Radiant Resistance (ISO 11612)	C4
Molten Aluminum (ISO 11612)	D3
Molten Iron (ISO 11612)	E3

Ordering Information

Length (m)	45.72
Minimum Order Quantity	50 Yards

Questions?

Please call Technical Sales Support or email us at sales@newtex.com

USA (585) 924-9135

INT (800) 836-1001